

General data			
Panel			2200 x 220 mm
Total thickness	EN 14354		± 13,5 mm
Numbers of panels per pack			4
Nested Lengths			Max. 1 plank out of 4
m ² per pack			1,936 m ²

Panel build up			
1. Finishing	UV cured Lacquer	Anti-scratch top coat	5 - 7 layers
2. Toplayer		PEFC controlled sources	2,5 (± 0,5) mm
3. Core board		PEFC controlled sources	Wooden core
4. Backing layer		PEFC controlled sources	2 mm
Tongue and groove		Wood Veneer	
		Length	Uniclic
		Width	Perfectfold 2.0



Warranty		
Domestic use	See warranty conditions	Lifetime
Uniclic - Perfectfold connection	See warranty conditions	Lifetime
Commercial		On request
"Stay Clean Technology" (lacquered products only)	See warranty conditions	15 years
"Stay Clean +" Water Resistance (lacquered products only)	See warranty conditions	15 years

Surface layer		
Wood species		Oak
Origin		Europe
Natural variance	Due to nature, visual surface can deviate from samples	
Surface treatments	cf catalogue/website	

Installation		Norm requirements	
Floating		On Pergo underlay	cf installation instructions
Glued to subfloor		Pergo MS polymer resin	cf installation instructions
General aspect of installed flooring			EN 14354 - Table 1
Dimensional stability	ISO 24339	Changes 30 - 85 % RH	Suitable
Underfloor heating	Suitable	cf special installation instructions	

Classification properties			
Water resistancy	ISO 4760	Qualitative rating for Recovery swell Quantitative rating for Recovery swell Joint leakage	1 < 0,1mm No leakage
Stain resistance	EN 13442	Floors with "Stay Clean Technology" (lacquered products only)	class 3 class 5
CE	EN 14342:2013	Notified Body	NB 0766 - EPH Dresden DOP: On pack
UKCA	EN 14342:2013	Approved Body	AB 0321 - Satra UK DOP: On pack
Castor chairs	ISO 4918	Tested with underlay	25.000
Slip resistance	CEN/TS 15676 : 2008	Dry Pendulum test	Depending on structure and surface treatment USRV 37-57
Emission of formaldehyde	EN 717-1		≤ E1
PCP	CEN/TR 14823:2004		≤ 5 ppm
Heat resistance	EN12664:2001		0,127 m².K/W
Reaction to fire	EN 13501-1		Cfl-s1

Ecological certificates		
AFFSET	A+	France
PEFC	PEFC/07-32-37	
EPD	On request	
F4* Compliant		
M1		Finland

