

DIMENSIONS

Collection	MODERN PLANK		CLASSIC PLANK	TILE
Width	217 mm		194 mm	327 mm
Length	1515 mm		1256 mm	1305 mm
Number of panels per pack	11 Panels		15 Panels	9 Panels
m ² per pack	3,616 m ²		3,655 m ²	3,841 m ²
Weight per pack	16,44 kg		16,61 kg	17,44 kg
Density	1782±50 kg/m ³		1782±50 kg/m ³	1782±50 kg/m ³
Total thickness	ISO 24346	2,5 mm	2,5 mm	2,5 mm
Top layer	ISO 24340	0,55 mm	0,55 mm	0,55 mm
Finishing	Advanced PU-Top coating with TitanV™ technology			

FACTORY WARRANTY

Usage class	EN ISO 10874		Class 33	
Product norm	ISO 10582 (EN 16511)			
CE / UK CA (floor)	EN 14041:2004 / AC:2006		DOP: see end label on pack	
CE / UK CA (wall)	EN 15102:2007 + A1:2011		DOP: see end label on pack	
Warranty	Floor	Residential use	See warranty conditions	25 years
	Floor	Commercial use	See warranty conditions	10 years - on request up to 15 years
	Wall	Residential use	See warranty conditions	10 years
	Wall	Commercial use	See warranty conditions	0 years - on request up to 5 years

GENERAL DATA

	METHOD	PARAMETERS	NORM REQUIREMENTS	PERGO VALUES
Wear resistance	EN 13329 - Annex E		≥ 2000 cycles	OK
Impact resistance	EN 13329 - Annex F		≥ 1600 mm	1800 mm
Scratch resistance	EN 16094		≤ MSR-A2 ≤ MSR-B2	MSR-A1 MSR-B2
Castor chairs	EN 425	25000 cycles	No delamination, no disturbance	OK
Displacement of furniture feet	EN 424	Foot 0,1 mm / 32 kg		No visible damage
Residual indentation	EN ISO 24343-1		≤ 0,1 mm	0,05 mm
Resistance against staining	EN 438-2	Acetone - Coffee -NaOH -H2O2 - Shoe Polish		grade 5 No change
Swelling	ISO 24336		≤ 18%	no swelling
Dimensional stability	ISO 23959	6 hrs at 80°C	< 0,25%	< 10,10%
		Cupping	< 2 mm	< 2 mm
Fire classification - floor	EN 13501-1			BF-s1
Fire classification - wall	EN 13501-1:2010			D-s3,d0
UV resistance	ISO 105 B02	Blue reference	Class >6	Class 8
Slip resistance	EN 13893			DS
	DIN 51130:2014 / XP P05-011	With Shoes	All structures	R10 / PC10
	DIN 51097:1992 / XP P05-011	Barefoot	All structures	Class B / PN18
	BS7976-2:2002+A1:2013	Wet	PTV value ≥ 36	PTV value ≥ 42 Low slip potential
		Dry	PTV value ≥ 36	PTV value ≥ 60 Low slip potential
	EN 12633:2003-Annex A		USRV	Class 2
Thermal resistance	EN 12667	Without PERGO underlay		0,015 m ² K/W
Floor heating	Appropriate for all standard heating systems IN cement flooring. Limited application with heating films and alternatives. Max contact temp ≤ 27°C. See separate installation instructions.			

Impact sound reduction ISO 712/2 ΔLw=2 dB

ENVIRONMENT & CERTIFICATES

Floorscore			SCS-FS-05190
AFFSET			A+
Finnish Building Emission	M1: Very low emission, odorless		Class M1
Formaldehyde emission	EN 14041:2004 / AC:2006	No added formaldehyde in production	< detection limit
TVOC 28 days	ISO 16000 part 9-6	AgBB requirement after 28 days <1000 µg/m ³	< 20 µg/m ³
Content	Heavy metals+ lead/cadmium		NOT present
DANGEROUS SUBSTANCES	Carcinogenic, mutagenic or reprotoxic substances class 1A and 1B (candidate list)		NOT present
REACH	Regulation (EC) No 1907/2006		Compliant
Plasticizer	Ortho-phthalate free plasticizer		
Recycled content	Only INTERNAL recycled material used		



UN 14041:2004 / AC:2006
Heterogeneous PVC Floorcoverings
ISO 10582:20018

UN 14041:2004 / AC:2006
Heterogeneous PVC Floorcoverings
ISO 10582:20018

UN 15102:2007 / A1:2011
Decorative Wallcoverings
roll and panel form products

EN 15102:2007 / A1:2011
Decorative Wallcoverings
roll and panel form products